



# MAYOR SPRAYED PLASTER

## READY-TO-SPRAY WHITE MORTAR FOR MANUAL OR MACHINE USE PRODUCT

**Description** **MAYOR SPRAYED PLASTER** is a cementations ready mix plaster, to carry out traditional plastering works in a clean and speedy manner, while keeping a homogeneous mix. Due to its content in additives, it allows better workability and curing. also it can be used in light inclination works (1 - 4) cm for surfaces and floors

**Uses** **MAYOR SPRAYED PLASTER** is particularly recommended for application by spraying machine.

It may be applied even on walls or ceilings on the following substrates:

- Concrete blocks, bricks, etc...
- Fair faced concrete
- Prefabricated concrete
- Traditional cementations plaster
- Light inclination works in surfaces and floors

**Advantages**

- interior application as a filler/skim coat.
- good filling properties.
- smooth surface produced.
- quick drying.
- higher filling thicknesses possible by adding cement.
- easy abrading properties.
- interior and exterior application as an intermediate spatter coat.
- applied by hopper gun.
- good spraying properties.
- almost odorless.
- conforms to Environmental Specifications .

**Product Data** form powder: Color Grey ( white and different color available upon request)  
Backing : 10 kg bag  
Storage Condition: 24 months after manufacturing date in original and non-open packaging , under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.



### TECHNICAL DATA

Wet mix life < 1hr  
Density 1.5 kg/l  
Chloride content Nil  
Coverage 10m<sup>2</sup>/10 kg for 1cm thickness  
complies with ASTM C1107

### APPLICATION DETAILS

**SURFACE PREPARATION**  
All substrates must be clean, sound, dust free, and free from all traces of oil and laitance. The traces of mould joints must be leveled. In case of smooth surfaces, a spatter dash slurry coat should be made.  
Before application all surfaces must be dampened.

### PRODUCT PREPARATION

Mayor Sprayed Plaster is mixed and applied on the surface by using special spraying machine.  
The Dosage of clean water may be 2 - 3 liters per 10 kg bag.

### PRODUCT APPLICATION

The plastering is leveled and finished like a usual plaster. For thickness more than 1.5cm, apply in 2 coats.  
After leveling, let the product dry before finishing it with a synthetic sponge.

### CURING

Protect the newly applied plaster from sunshine and wind.  
The new plaster has to be cured with water for at least three days by spraying 3 to 4 times daily.

### SAFETY PRECAUTIONS

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust.  
Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

+249-912981928  
+249-918883330  
+249-929888333

✉ husam@mayoreng.com  
f مصنع مايور لكيمائيات البناء  
مايور كيم

🌐 www.mayoreng.com  
☎ +249-9183478259

📍 المصنع: المنطقة الصناعية الباكير مربع (1) - عقار رقم ٦٦  
الإدارة: الخرطوم تقاطع شارع الصحافة زلط مع شارع ١٥  
العمارات - عمارة مايور الطابق الأول